



TECHNICAL DATA SHEET

LDPE 8020

Properties LDPE regranulate

Test	Property	Value	Unit	Conditions	Norm
Tensile testing	Max. tensile stress	12	MPa	23°C / 50% RH	ISO 527-2
	Modulus of elasticity (Youngs)	350	MPa	23°C / 50% RH	ISO 527-2
	Max. tensile strain	>50	%	23°C / 50% RH	ISO 527-2
Impact testing	IZOD impact strength	t.b.d.	kJ/m ²	23°C / 50% RH	ISO 180
	Notched IZOD impact strength	t.b.d.	kJ/m ²	23°C / 50% RH	ISO 180
MFI	MFI	3-4	g/10min	190°C/5.00 kg	ISO 1133

DISCLAIMER:

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.