

## astics k

# artner in secondary raw materials

## TECHNICAL DATA SHEET PP COPOLYMER

**TYPE 8220** 

### **Properties**

PPc 8220 (PP copolymer)

PPC 6220 (PP Copolymer)					
Test	Property	Value	Unit	Conditions	Norm
Tensile testing	Max. tensile stress	27	MPa	23°C / 50% RH	ISO 527-2
	Modulus of elasticity				
	(Youngs)	1300	MPa	23°C / 50% RH	ISO 527-2
	Max. tensile strain	10	%	23°C / 50% RH	ISO 527-2
Impact testing	Notched Izod impact	5	kJ/m2	23°C / 50% RH	ISO 180
	strength				
MFR	MFI	22-27	g/10min	230°C/2.16 kg	ISO 1133

## DISCLAIMER:

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.